



DIEHCO sarl

ZA BERROUETA
F-64122 URRUGNE

diehco@diehco.com
TEL: (33) 5 59 85 14 72
FAX: (33) 5 59 85 14 73

PROPORTION DE RESINE EN FONCTION DE LA TEMPERATURE

DENSITE RESINE : 1 LITRE = 1,15KG.

TEMPERATURE	10<14°	14<28°	>28°
%SBR POUR 1 SAC DE 25KG	11% =2,60KG =2,25L	13% =3,00KG =2,60L	14% =3,40KG =2,90L
%EPDM POUR 1 SAC DE 25KG	18% =4,50KG =4,00L	20% =5,00KG =4,35L	22% =5,50KG = 4,75L